## HARDWOOD FLOORING



TECHNICAL DETAILS								
Notes:			Pattern: Plank			Color: Sand		
PRODUCT INFO			PACKAGING			STRUCTURE		
Species Finish Structure Joint Bevel Surface Grade DIMENSIONS Thickness Width Row Length Shorts	White Europea UV Silk Engineered (2- T&G Micro (0,5 mm Light Brush Character 15 mm (5/8") 190 mm (7,5") 1900 mm (6,25) 25%	-layer) )	BOX	1294 kg (2852 1050 mm (3,45')	2,888 m <sup>2</sup> (31 ft <sup>2</sup> ) 200 mm (7,9") 10) 115,52 m <sup>2</sup> (1243 ft <sup>2</sup> ) 1930 mm (6,4')	2-layer Engineered Construction * Solid wood 4 mm ** Plywood ***		
FINISH						Description		
Sheen \ Gloss Look Feeling Type Wear resistance Scratch resistance Slip resistance Resistance to chemical agents Maintenance Repairability TECHNICAL INFORMATION Characteristics (EN 14342) Formaldehyde emission class E1; ULEF Pentachlorophenol content None Thermal resistance 0,118 m2 K\W			Matte Semi-open pores, wire brushed Transfer warms of natural wood UV cured modified polyurethane-acrylate High Medium 50 (SRV dry) Class 5 (Except blue ink) Maintenance free Easy  Deviation on Thickness 0,2 mm Deviation on Width 0,2 mm Height Difference 0,2 mm		al wood rethane-acrylate 0,2 mm	antique woodworm holesauthentic naturaloak texturediversecolorvariationsapwoodunlimited burlsbrown streakstight knotsCharacter Grade creates an effect of antique wood and emphasizes authentic natural oak texture. Planks may contain diverse color variation, sapwood, unlimited burls, brown streaks, tight knots and properly filled open knots, warm holes as well as other imperfections in the face work (torn grain) to design advantage.		
Thermal condu Fire resistance	uctivity	0,161 W\(m K) Dfl-s1	Cup Bow Spring		<pre>&lt;0,2 mm &lt;0,2% of width &lt;0,5% of length &lt;0,1% of length</pre>	h		

## **PRODUCT USE**

## INSTALLATION **STORAGE & USE** Glue down over concrete, plywood or wooden subfloor or nail down +22°C 72°F over wooden subfloor. Semifloating installation as well. 40-65% Applicable above, on and below ground level. +18°C Suitable for underfloor heating. Air Humidity 40-65% Temperature +18°C ... +22°C (64°F ... 72°F) **CARE & MAINTENANCE DESCRIPTIONS & IMAGERY** Maintenance of hardwood floors with UV Silk assumes normal (daily if necessary) cleaning from Flooring colors displayed in digital dust and grit using a vacuum, followed by a thorough cleaning with floor cleaner. Floor surface platforms may vary according to areas that receive the most traffic and get worn down quicker, such as areas by the front door, the color settings of the monitor hallways, kitchens etc. should be periodically renewed with oil. you are using.

ME Decor Group OÜ Harju maakond, Tallinn, Pohja-Tallinna linnaosa, Kopli tn 27, Estonia 10412 VAT-LT100014600119 E-mail: info@me-decor.com www.me-floor.com



nw

a NO ADDED formaldehyde

